

Borchi® Gen 1252 / Borchi® Gel PN

Higher Inorganic Pigment Loading, Long Term Viscosity Stability & Anti-Settling Performance


- No settling and improved viscosity variance over time after extended heat age stability
- No change in gloss or contrast ratio
- High opacity
- Strong tint strength

75% TiO₂ Concentration

Excellent Viscosity Stability with Borchi® Gen 1252 and Borchi® Gel PN


75% Ti- Pure® R706

Borchi® Gen 1252 / Borchi® Gel PN




75% Kronos 2310

Borchi® Gen 1252 / Borchi® Gel PN



75% Tronox® 828


Borchi® Gen 1252 / Borchi® Gel PN




2-Week, 50° C Stability Test



Settling
Control



Free-Flowing
Borchi® Gen 1252 & Borchi® Gel PN



Settling
Control



Free-Flowing
Borchi® Gen 1252 & Borchi® Gel PN

WB Concentrate 75% TiO₂

Water	21.88
Borchi® Gen 1252 (100%)	2.25
AMP 95	0.12
Borchers® AF 1171	0.25
Borchi® Gel PN	0.50
TiO ₂	75.00
TOTAL	100.00
AOP	3.00%

Borchi® Gen 1252 / Borchi® Gel PN

Higher Inorganic Pigment Loading, Long Term Viscosity Stability
& Anti-Settling Performance

70% TiO₂ Concentration

Formulation

	Borchi® Gen 1252 / Borchi® Gel PN	Fumed Silica
TiO ₂	70.00	70.00
Borchi® Gen 1252 (100%)	2.10	3.50
AMP 95	0.10	0.15
Borchers® AF 1171	0.25	0.25
Borchi® Gel PN	0.50	
Fumed Silica		0.30
DI Water	27.05	25.80
TOTAL	100.00	100.00
%DOP	3.00	5.00

Disperse in the Lau for 1 hr
Concentrate to Glass Beads 1:1

Evaluations in Flat Exterior and Semi-Gloss Alkyd


Exterior Flat (gloss clear 85° = 1.5)	1 week		2 months	
	3% DOP	5% DOP	3% DOP	5% DOP
	0.5% PN	Fumed Silica	0.5% PN	Fumed Silica
Contrast Ratio (L*B/L*W)	0.98	0.99	0.99	0.99
Gloss 85° Leneta	4	15	4	10

Alkyd Semi-Gloss (gloss clear 60° = 10)	1 week		2 months	
	3% DOP	5% DOP	3% DOP	5% DOP
	0.5% PN	Fumed Silica	0.5% PN	Fumed Silica
Contrast Ratio (L*B/L*W)	0.99	0.99	0.99	0.99
Gloss 60° Leneta	10	14	10	14

Stable Gloss Values Over Time

Viscosity Stability

Borchi® Gel PN vs Fumed Silica Viscosity Stability σ (CP)



Order your sample at:
www.borchers.com

+91 98338 68167
bhupesh.marathe@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

Milliken™